

ABSTRACT OF THE DISCLOSURE

A pair of primary semi-hollow bodies formed by primary injection molding are united together by the molten resin injected for secondary injection molding to fill a joining
5 space defined about the butt ends of the primary semi-hollow bodies having their open ends butted against each other. The molten resin for secondary molding fills the space between the butt ends, or the notch portion, too. Alternatively, the molten resin is compressed after filling the joining space and
10 the space between the butt ends.